

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C23C 22/34, 22/36	A1	(11) International Publication Number: WO 95/10641 (43) International Publication Date: 20 April 1995 (20.04.95)
(21) International Application Number: PCT/US94/11684 (22) International Filing Date: 14 October 1994 (14.10.94) (30) Priority Data: 08/137,583 15 October 1993 (15.10.93) US (71) Applicant: CIRCLE-PROSCO, INC. [US/US]; 2017 Yost Avenue, Bloomington, IN 47403 (US). (72) Inventor: TOMLINSON, Charles, E.; 970 Conservation Club Road, Martinsville, IN 46151 (US). (74) Agents: THOMAS, Timothy, N. et al.; Woodard, Emhardt, Naughton, Moriarty & McNett, Bank One Center/Tower, Suite 3700, 111 Monument Circle, Indianapolis, IN 46204 (US).		(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, NO, NZ, PL, RO, RU, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report.</i>
(54) Title: CONVERSION COATINGS FOR METAL SURFACES (57) Abstract <p>A conversion coating for aluminum, ferrous and magnesium alloyed materials includes zirconium, fluoride and calcium ions. The coating is preferably at a pH of between about 2.6 and about 3.1, and may optionally include phosphates, polyphosphates, tannin, boron, zinc and aluminum. A sequestering agent to complex dissolved iron, and a crystal deformation agent such as ATMP are also preferably included.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

CONVERSION COATINGS FOR METAL SURFACES

FIELD OF THE INVENTION

The present invention relates generally to coatings for metal surfaces, and more particularly to conversion coatings
5 for aluminum.

BACKGROUND TO THE INVENTION

A variety of chemical conversion coatings for aluminum or other metal surfaces are known to the art. All of these conversion coatings prevent metal surfaces from being
10 converted to their metal oxide by corrosion by replacing or modifying the outer surface layer of the base metal. A corrosion resistant outer layer is thereby provided, while often simultaneously providing a surface for improved paint or other organic coating adhesion. Conversion coatings may
15 be applied by a "no-rinse" process in which the metal surface to be coated is cleaned and the conversion coating is dipped, sprayed or rolled on, or they may be applied as one or more coats which are subsequently rinsed to remove undesirable residues from the coating process.

20 Many conversion coatings are chromate-based compositions. In general, chromate-based conversion coatings are acidic, aqueous compositions comprising chromic acid and chemical supplements. In order to improve deposition of the coating to the metal surface, alkali metal salts and/or
25 mineral acids may be added to adjust solution pH.

More recently, chromate-free conversion coatings have also been developed. These coatings are especially useful for applications, such as coating aluminum food or beverage cans, in which it is particularly desirable to avoid

-2-

potentially toxic chromates. Chromate-free conversion coatings typically employ a Group IVA metal such as titanium, zirconium or hafnium, a source of fluoride ion and a mineral acid for pH adjustment. Conversion coatings of this sort are typically clear in color, and are commonly used to prevent the blackening that normally occurs when aluminum is boiled in water during pasteurization.

For example, U.S. Patent No. 3,964,936 to Das discloses the use of zirconium, fluoride, nitric acid and boron to produce a conversion coating for aluminum. U.S. Patent No. 4,148,670 to Kelly discloses a conversion coating comprising zirconium, fluoride and phosphate. U.S. Patent No. 4,273,592 to Kelly discloses a coating comprising zirconium, fluoride and a C₁₋₇ polyhydroxy compound, wherein the composition is essentially free of phosphate and boron. U.S. Patent No. 4,277,292 to Tupper discloses a coating comprising zirconium, fluoride and a soluble vegetable tannin.

U.S. Patent No. 4,338,140 to Reghi discloses a conversion coating comprising zirconium, fluoride, vegetable tannin and phosphate, and optionally including a sequestering agent to complex hard water salts such as calcium, magnesium and iron. U.S. Patent No. 4,470,853 to Das et al. discloses a coating comprising zirconium, fluoride, vegetable tannin, phosphate and zinc. U.S. Patent No. 4,786,336 to Schoener et al. discloses a coating comprising zirconium, fluoride and a dissolved silicate, while U.S. Patent No. 4,992,116 to Hallman discloses a conversion coating comprising a fluoroacid of zirconium and a polyalkenyl phenol.

It can be seen from the above that the compositions of the prior art have not combined Group IIA metals such as calcium with Group IVA metals such as zirconium to provide corrosion resistant coatings. In fact, prior art compositions have expressly avoided Group IIA metals since at low concentrations such metals are known to cause scaling from alkali metal precipitates. As was noted above, U.S.

-3-

Patent No. 4,338,140 to Reghi uses a sequestering agent such as EDTA to complex hard water components such as calcium and magnesium.

It should further be noted that the conversion coatings
5 of the prior art have not proven particularly effective for certain applications. For example, formed aluminum parts used in automotive heat exchange devices (such as air conditioner evaporators) which are exposed to highly corrosive environments have not been effectively treated
10 using known cromate-free coatings.

A need therefore exists for improved conversion coatings for providing a high level of corrosion resistance to aluminum and other metals, such as magnesium and ferrous alloys, used in aggressive environments. The present
15 invention addresses that need.

-4-

SUMMARY OF THE INVENTION

The present invention provides improved conversion coatings based on Group IVA metals such as zirconium by combining the Group IVA metal with a group IIA metal such as calcium. In one aspect of the invention, an aqueous conversion coating is provided comprising between about 10 ppm and about 5,000 ppm zirconium, between about 50 ppm and about 1300 ppm calcium, and between about 10 ppm and about 6,000 ppm fluoride; the composition having a pH of between about 2.0 and about 5.0. The coating may optionally include polyphosphates, tannin, phosphates, boron and zinc; a sequestering agent to complex dissolved iron, and a crystal deformation agent such as ATMP may also be included.

One object of the present invention is to provide improved conversion coatings for aluminum automotive parts such as wheels, body panels and heat exchange devices.

Further objects and advantages of the present invention will be apparent from the following description.

-5-

DESCRIPTION OF THE PREFERRED EMBODIMENT

For the purpose of promoting an understanding of the principles of the invention, reference will now be made to preferred embodiments and specific language will be used to describe the same. It will nevertheless be understood that
5 no limitation of the scope of the invention is thereby intended, such alterations and further modifications in the illustrated embodiments, and such further applications of the principles of the invention as illustrated herein being
10 contemplated as would normally occur to one skilled in the art to which the invention pertains.

As indicated above, the present invention relates generally to chromate-free compositions which provide a highly corrosion resistant coating on the surface of metal
15 substrates. In particular, coatings based on Group IVA metals such as zirconium are disclosed, with the traditional performance of Group IVA coatings being improved by adding calcium to the mix. The inventive compositions produce a hydrophilic, corrosion resistant coating on iron, aluminum
20 and magnesium while providing a surface that gives improved adhesion of paint and other organic coatings.

In one aspect of the present invention a corrosion resistant conversion coating is provided comprising a Group IVA metal such as titanium, zirconium or hafnium, a Group
25 IIA metal such as calcium or magnesium, and a source of fluoride ions. The composition is preferably provided at a pH of between about 2.0 and 4.5, most preferably between about 2.6 and 3.1.

As indicated, the Group IVA metal may be titanium,
30 zirconium or hafnium. (Group IVA refers to the IUPAC nomenclature; the corresponding CAS designation for these metals is Group IVB. Alternatively, these metals may be designated merely as Group 4.) In most applications zirconium is used, due primarily to its commercial

-6-

availability and lower cost. Other Group IVA metals may be used as desired for a particular commercial application.

The zirconium or other Group IVA metal is provided in ionic form which is easily dissolved in the aqueous coating composition. For example, K_2ZrF_6 , H_2ZrF_6 or $Zr(O)(NO_3)_2$ may effectively be used. Note that the source of Group IVA metal ion may also be a source of fluoride ion, commonly an alkali metal fluorozirconate salt. Potassium hexafluorozirconate is most preferred.

10 The Group IIA metal may be calcium, magnesium, beryllium, strontium or barium, with calcium being preferred in one embodiment. The Group IIA metal may be provided as any of the many inorganic hydroxides or salts available, including the nitrates, sulfates, fluorides, etc. For example, 15 $Ca(OH)_2$, $Ca(NO_3)_2$, etc., may be used, with calcium nitrate being most preferred in one embodiment.

A source of fluoride ion is also included to maintain the solubility of metals in solution. The fluoride may be added as an acid (e.g., HF), as any of the many fluoride salts 20 (e.g., KF, NaF, etc.), as the complex metal fluoride of the Group IVA metal, or in any other form which will donate fluoride to the working solution. Most preferably the fluoride is added as K_2ZrF_6 and KF.

The fluoride is preferably present in a molar ratio of at 25 least 4 moles fluoride to each mole of metal. The concentration of fluoride in the working solution is selected such that the metals remain soluble and little or no etching of the substrate occurs. The particular fluoride level is also selected according to the pH and metal concentration of 30 the coating solution, knowing that the fluoride will move from the higher order metal fluorides to the lower order and preferentially to the metallic (oxide) surface. A small amount of etching of an oxide surface is acceptable, but much of the metal oxide present on the surface prior to coating 35 should be retained to give additional protection in a

-7-

corrosive environment and to extend the life of the coating solution.

The pH of the coating is normally between about 1.5 and 5.0, preferably between about 2.0 and 4.0, most preferably
5 between about 2.6 and 3.1. The pH may be adjusted by adding a Group IVA metal acid, an acid fluoride, or other mineral acids such as HNO_3 , H_2SO_4 , etc. Most preferably, HNO_3 is used. Generally, higher levels of metal concentration necessitate lower pH levels and, with
10 increasing levels of metal and acid, a heavier coating is obtained under these conditions.

The temperature of the working solution preferably ranges from about 70°F to about 160°F. Appropriate working solution temperatures for particular applications may be selected by
15 persons skilled in the art without undue experimentation.

Acceptable coatings can be formed from solutions containing from $1.5 \times 10^{-4}\text{M}$ to $5.5 \times 10^{-2}\text{M}$ Group IVA metals, with $2.5 \times 10^{-4}\text{M}$ to $3.0 \times 10^{-2}\text{M}$ Group IIA metals. The best ratio of Group IVA to Group IIA metal
20 depends on the method of coating solution contact (spray, dip, flood, etc.), working bath temperature, pH, and fluoride concentration. For example, for a five minute immersion at 80° to 140°F, 150 to 600 ppm Zr, 40 to 300 ppm Ca and 200 to 740 ppm F^- , at a pH from 2.6 to 3.1, gives superior
25 corrosion protection.

Working solutions can be made up to the solubility limits of the components in combination to provide acceptable coatings. Lower levels are preferred, however, as dissolved substrate metal ions entering the coating solution during
30 processing may cause precipitation of bath components. As will be discussed further, when bath component precipitates are formed, the addition of a chelant such as Versenex 80 to a bath for treatment of ferrous substrate will yield a soluble ion complex with dissolved iron, extending the life
35 and efficiency of the working solution.

-8-

In a second aspect of the invention the quality of the coating is improved by adding, e.g., phosphates, polyphosphates, tannin, aluminum, boron, zinc, a sequestering agent to complex dissolved iron, and a crystal deformation agent such as ATMP. In the most preferred embodiment, all of these components are included.

The addition of a tripolyphosphate (as $\text{Na}_5\text{P}_3\text{O}_{10}$ or other polyphosphate salt) will assist in maintaining high levels of calcium in the treatment bath, as soluble calcium complexes will form with tripolyphosphate and provide a "reservoir" of calcium to the solutions.

The addition of phosphate to the working bath also adds both to corrosion protection and to paint adhesion to the coating obtained. It is commonly believed that the incorporation of phosphates into certain conversion coatings enhances protection from "pitting" corrosion; as when a pit is initiated in a corrosive environment, the phosphate present will first dissolve into the pit area and, there, form insoluble salts with base (substrate) metal ions or other coating components, effectively sealing the pit.

Organic additives such as tannic acid or vegetable tannins in plating and chemical conversion coating systems are beneficial in promoting uniformity of coating, organic coating adhesion, and corrosion resistance. Tannic acid and vegetable tannins may be incorporated into the treatments disclosed here and do give the benefits listed above. Tannic acid shows beneficial effects in a very broad range, from 10 ppm to its solubility limit. At higher levels, the coating becomes very golden brown as much of the tannate has become incorporated into the coating. Optimum levels of tannic acid and vegetable tannins are from 50 to 500 ppm.

The addition of boron in the form of boric acid or a borate salt to the working solution improves certain properties of the coating, such as corrosive resistance. Borate anions in the presence of calcium will form a

continuous polymeric oxide structure with the basic CaB_2O_4 composition. This, along with the zirconium and zirconate matrix, is believed to be a source of improved corrosion protection. The preferred range for boron is 50 to 100 ppm, typically present at 10 to 200 ppm.

The addition of zinc to the working solution produces coatings with improved corrosion resistance. It is believed the zinc accelerates coating deposition and, when incorporated into the coating (if reduced) may provide galvanic protection to the metal substrate. The typical range for zinc is 5 to 100 ppm, preferably 10 to 30 ppm.

Aluminum added to the working solution increases the rate of deposition of insoluble salts in the coating. Aluminum may be added in any form of soluble aluminum salt, preferably as a hydrated aluminum nitrate. Typically, aluminum may be present at 50 to 1000 ppm, preferably at 100 to 200 ppm.

It should be noted that the presence of iron in working solutions for aluminum and other metals may decrease the corrosion protection obtained. A chelant such as EDTA, triethanolamine, or Versenex 80 will preferentially complex the iron in solution, at the preferred pH values stated, and inhibit its incorporation into the conversion coatings.

Additionally, calcium salts which may form in the higher end of the temperature range mentioned may be more soluble at the lower temperatures and, therefore, the working solution should be used at the lower end of the temperature range when the calcium content of the working solution is at the high end of the levels stated.

Crystal deformation additives such as nitrilotris (methylene)triphosphoric acid function to reduce the average crystal size of the deposited coating, providing a more uniform surface texture. This promotes even deposition of coating and enhances paint adhesion to the surface. An additive such as ATMP may be used in a broad concentration

-10-

range (10 to 2000 ppm) and is preferably used from 50 to 200 ppm.

Working solutions composed of mixture(s) of the above components may be applied by spray, dip, or roll coat application. After the coating has formed, the surface should be rinsed with clean water. The rinse(s) may be deionized or tap water and should remove any soluble salts which might be present on the surface.

The surface obtained is hydrophilic and may be coated with an organic or silicate coating. Adhesion of organic coatings is improved when compared to untreated metal. Treatment with a silicate, preferably a 1 to 15 weight % sodium silicate solution, extends the life of the metallic substrate in a corrosive environment.

It is to be appreciated that siccative coatings which form an organic barrier may also be necessary for decorative purposes of the final product. Silicates (such as Sodium Silicate Grade #40 at 0.5% to 20% in water) deposit and react with the formed coating to provide additional corrosion protection while maintaining a hydrophilic surface. The silicate dries and forms a network of siloxyl linkages. The corrosion protection is enhanced by the silicate as with the siccative type coatings. The siccative type coatings usually leave a surface which is hydrophobic.

Reference will now be made to specific examples using the processes described above. It is to be understood that the examples are provided to more completely describe preferred embodiments, and that no limitation to the scope of the invention is intended thereby.

EXAMPLE 1

A calcium-free conversion coating solution was prepared in distilled water as follows. Potassium hexafluorozirconate (1.0 grams K_2ZrF_6 per liter, providing approximately 313 ppm Zr and approximately 402 ppm F) was provided in aqueous solution at a pH of 2.6 with nitric acid. A calcium-free conversion coating was formed.

-11-

EXAMPLE 2

A conversion coating solution was prepared in distilled water as follows. Potassium hexafluorozirconate (1.0 grams K_2ZrF_6 per liter, providing approximately 313 ppm Zr and approximately 402 ppm F) was added to a solution of calcium hydroxide (148 mg $Ca(OH)_2$ providing approximately 80 ppm Ca) and nitric acid. The solution pH was adjusted to 2.6 with 0.273 ml 42° Baume HNO_3 . A conversion coating according to the present invention was formed.

EXAMPLE 3

10 A preferred embodiment of a conversion coating solution was prepared in distilled water as follows. Potassium hexafluorozirconate (1.0 grams per liter providing approximately 313 ppm Zr and approximately 402 ppm F) was
15 added to a solution containing 148 mg $Ca(OH)_2$, 500 mg $Na_2B_4O_7 \cdot 10H_2O$, 1.0 mL 42° Baume HNO_3 , 500 mg sodium tripolyphosphate, 200 mg $KF \cdot 2H_2O$, and 100 mg of tannic acid per liter aqueous solution.

EXAMPLE 4

20 Aluminum (3003) panels were treated with the basic conversion coatings of Examples 1-3 (two panels for each example coating) for 5 minutes at 140°F. The panels were oven dried at 300°F for 5 minutes.

One panel was taken from each of the above sets and
25 treated (5 minute dip at 120°F) with a 10% by weight Grade 40 sodium silicate solution in deionized water. After the sodium silicate treatment, the panels were dried for 5 minutes at 300°F.

All panels were exposed to a solution comprising 5% NaCl
30 and 8.0×10^{-4} M acetic acid (pH = 3.1) at 90-92°F. This test is commonly referred to as SWAAT.

Results are given in the table below, giving the percent area showing pitting (in a 10x20 grid) of the treated panels for up to four days exposure.

-13-

EXAMPLE 5

Evaporators used in air conditioning units were coated with the preferred embodiment of the coating. The evaporators were treated at 140°F solution temperature by immersion for 5 minutes followed by a 10% grade 40 silicate treatment at 120°F. The evaporators were thoroughly rinsed with tap water for 30 seconds and dried at 300°F for 10 minutes. The evaporators were tested and passed requirements for SWAAT (500 hours without loss of refrigerant pressure) and neutral salt (1,000 hours without perforation) testing. The units also passed requirements for "wet ΔP " tests. (The wet ΔP test measures the drop in air pressure from one side of the evaporator to the other in 50% and 90% humidity environments.) No difference was seen between the two levels, indicating excellent watershedding capability of the coating and excellent hydrophilicity.

While the invention has been illustrated and described in detail in the drawing and foregoing description, the same is to be considered as illustrative and not restrictive in character, it being understood that only the preferred embodiment has been shown and described and that all changes and modifications that come within the spirit of the invention are desired to be protected.

-14-

CLAIMS

We claim:

1. An aqueous composition for coating aluminum, ferrous or magnesium alloys, comprising:

5 (a) between about 10 ppm and about 5,000 ppm, based on the aqueous composition, of dissolved Group 4 metal ions selected from the group consisting of titanium, zirconium and hafnium;

10 (b) between about 80 ppm and about 1300 ppm, based on the aqueous composition, of dissolved Group 2 metal ions selected from the group consisting of magnesium and calcium;

(c) between about 10 ppm and about 6,000 ppm, based on the aqueous composition, of dissolved fluoride ions; and

(d) water;

15 said composition having a pH of between about 2.0 and about 5.0.

2. A aqueous composition according to claim 1 wherein the Group 4 metal is zirconium.

20 3. A aqueous composition according to claim 1 wherein the Group 2 metal is calcium.

4. A coating composition according to claim 3 wherein said calcium ions are present in the amount of between about 100 ppm and about 500 ppm of the aqueous composition.

25 5. A coating composition according to claim 3 wherein said calcium ions are present in the amount of between about 150 ppm and about 250 ppm of the aqueous composition.

6. A coating composition according to claim 3 wherein said zirconium ions are present in the amount of between about 200 ppm and about 1,000 ppm of the aqueous composition.

-15-

7. A coating composition according to claim 3 wherein said zirconium ions are present in the amount of between about 200 ppm and about 400 ppm of the aqueous composition.

8. A coating composition according to claim 3, and
5 further including a source of tripolyphosphate ions.

9. A coating composition according to claim 8 wherein said source of tripolyphosphate ions is sodium tripolyphosphate.

10. A coating composition according to claim 9 wherein
10 said tripolyphosphate ions are present in the amount of between about 60 ppm to about 4,400 ppm.

11. A coating composition according to claim 10 wherein said tripolyphosphate ions are present in the amount of between about 150 ppm to about 200 ppm.

15 12. A coating composition according to claim 3, and further including at least about 10 ppm of tannic acid or vegetable tannin.

13. A coating composition according to claim 12 wherein said tannic acid or vegetable tannin is present in the amount
20 of about 50 ppm to about 200 ppm.

14. A coating composition according to claim 3, and further including a sequestering agent in an amount effective to complex essentially all dissolved iron present in the composition.

25 15. A coating composition according to claim 3, and further including a source of boron.

-16-

16. A coating composition according to claim 15 wherein said boron is present in the amount of between about 10 ppm to about 200 ppm.

5 17. A coating composition according to claim 16 wherein said boron is present in the amount of between about 50 ppm to about 100 ppm.

10 18. A coating composition according to claim 3 and further including a phosphate salt in an amount effective to provide a phosphate concentration of between about 10 ppm to about 600 ppm.

19. A coating composition according to claim 18 wherein said phosphate salt is present in an amount effective to provide a phosphate concentration of between about 150 ppm to about 300 ppm.

15 20. A coating composition according to claim 3 and further including zinc ion at a concentration of between about 10 ppm to about 100 ppm.

20 21. A coating composition according to claim 20 wherein said zinc ion is present at a concentration of between about 20 ppm to about 30 ppm.

22. A coating composition according to claim 3 wherein said composition has a pH of between about 2.6 and 3.1.

23. A coating composition according to claim 3 and further including a crystal deformation agent.

25 24. A coating composition according to claim 23 wherein said crystal deformation agent is nitrilotris (methylenetriphosphonic acid (ATMP)).

-17-

25. A coating composition according to claim 3 and further including dissolved aluminum ion at a concentration of between about 10 and about 3,000 ppm.

26. A coating composition according to claim 25 wherein
5 said aluminum is present at a concentration of between about 100 and 600 ppm.

27. A method of treating metal, comprising applying to the metal an aqueous coating composition comprising:

- 10 (a) between about 10 ppm and about 5,000 ppm, based on the aqueous composition, of dissolved metal ions selected from the group consisting of titanium, zirconium and hafnium;
(b) between about 80 ppm and about 1300 ppm, based on the aqueous composition, of dissolved metal ions selected from the group consisting of magnesium and calcium;
15 (c) between about 10 ppm and about 6,000 ppm, based on the aqueous composition, of dissolved fluoride ions; and
(d) water;

said composition having a pH of between about 2.0 and about 5.0.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/11684

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :C23C 22/34, 22/36

US CL :148/247

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 148/247

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5,139,586 (Das) 18 August 1992.	

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

Special categories of cited documents:			
A	document defining the general state of the art which is not considered to be of particular relevance	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
E	earlier document published on or after the international filing date	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O	document referring to an oral disclosure, use, exhibition or other means		
P	document published prior to the international filing date but later than the priority date claimed	*Z*	document member of the same patent family

Date of the actual completion of the international search

13 DECEMBER 1994

Date of mailing of the international search report

06 JAN 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

SAM SILVERBERG

Telephone No. (703) 308-1974